1026

Nonresulfurized carbon steels 1026 steel chemical information,mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, We can produce round bars, forged rings, forged cakes, flat bars, tubes, sheets, plates, steel wires, steel strips, steel coils, etc. The size can be customized, the maximum order quantity is 100Kg. It also contains the use of **1026**,such as it is commonly used in bars, sheet,plates, steel coils, steel pipes,forged and other materials application.

Data Table for Grades Structural Steel Nonresulfurized carbon steels 1026

1026 Standard Number		
ITEM	Standard Number	Descriptions
1	A 1040 (2010)	Standard Guide for Specifying Harmonized Standard Grade Compositions for Wrought Carbon, Low-Alloy, and Alloy Steels
2	A 29/A 29M (2012)	Steel Bars, Carbon and Alloy, Hot-Wrought, General Requirements for
3	A 510/A 510M (2011)	General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel
4	A 512 (2006)	Cold-Drawn Buttweld Carbon Steel Mechanical Tubing
5	A 513/A 513M (2012)	Standard Specification for Electric-Resistance-Welded Carbon and Alloy Steel Mechanical Tubing
6	A 519 (2006)	Seamless Carbon and Alloy Steel Mechanical Tubing
7	A 576 (1990)	Steel Bars, Carbon, Hot-Wrought, Special Quality
8	A 830/A 830M (2011)	Plates, Carbon Steel, Structural Quality, Furnished to Chemical Composition Requirements
9	SAE J 1397 (1992)	Estimated Mechanical Properties and Machinability of Steel Bars
10	SAE J 403 (2009)	Chemical Compositions of SAE Carbon Steels
11	SAE J 412 (1995)	General Characteristics and Heat Treatments of Steels

1026 Chemical composition(mass fraction)(wt.%)		
Chemical	Min.(%)	Max.(%)

C	0.22	0.28
Mn	0.60	0.90
P		0.040
S		0.050

1026 Physical Properties		
Tensile strength	115-234	?b/MPa
Yield Strength	23	? 0.2 ?/MPa
Elongation	65	?5? (%)
?	-	?? (%)
Akv	-	Akv?/J
HBS	123-321	-
HRC	30	-

1026 Mechanical Properties		
Tensile strength	231-231	?b/MPa
Yield Strength	154	? 0.2 ?/MPa
Elongation	56	?5?(%)
?	-	??(%)
Akv	-	Akv?/J
HBS	235-268	-
HRC	30	-

1026 Heat Treatment Regime				
Annealing	Quenching	Tempering	Normalizing	Q & T
?	?	?	?	?

1026 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	?8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

We can produce Structural Steel the specifications follows:

Note:
(1) listed in the table apex diameter (d), to steel thickness (a) multiples said.
(2) in the ASTM A6 standard specified scope can meet any additional conditions.
(3) from the standard for 50 mm (2 in).
Mechanical properties
Mechanische Eigenschaften
Caracteristiques mecaniques
ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale
Rm Tensile strength / Zugfestigkeit / Resistance a la traction
A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal
J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar:
Diameter : 1mm-2000mm
Square bar:
Size: 50mm * 50mm-600mm *600mm
Plate steel/flat bar:
Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm
Tube/pipe:
Size: OD: 6-219mm WT: 1-35 mm.
Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm
Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm
Length: We can supply any length based on the customer's requirement.
Forging/hot rolling/ extrusion of steel.

Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes
Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement
Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement
Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode.
Ultrasonic inspection: 100% ultrasonic inspection for any inperfections or based on the customer's requirement.
UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402
Excellent service for all kinds of industries, with advantages of technologies, equipment and price.
We serve you with our honesty, integrity, and professionality.